



Tremco Commercial Sealants & Waterproofing  
 3735 Green Road  
 Beachwood, OH 44122  
 US: 800.852.9068  
 Canada: 800.363.3213  
 www.tremcosealants.com

We certify that ExoAir 210AT has been tested to the following ASTM standards and does conform to the specification requirements.

Property	Description	
Type	Acrylic sheet with nonwoven facer	
Color	gray	
Solids	100%	
Facer Basis Weight	2.95 oz/sy (100 gsm)	
Application	Self-adhered	
Storage Temperature	40 to 100 °F (5 to 37 °C)	
Application Temperature	Above 20 °F (-7 °C) and rising.	
Service Temperature	Intermittent Exposure up to 180 °F (86 °C)	
Property	Test Method	Typical Values
Maximum V.O.C.	Method 310	2 g/L
Air Leakage of material	ASTM E2178; Free Film Method @ 75 Pa	0.003 cfm/ft <sup>2</sup> (0.02 L/(s•m <sup>2</sup> ))
Water Vapor Transmission	ASTM E96 Wet Cup	16.9 US Perms
Water Resistance	AATCC-127	Pass
Adhesion	ASTM D4541	22.9 psi
Resistance to Puncture	ASTM E154	≥40 lbf
Peel Adhesion (72 hr)	ASTM D3330 Method F	
	Stainless Steel	5.2 lb <sub>f</sub> /in
	Plywood	7.25 lb <sub>f</sub> /in
	OSB	4.25 lb <sub>f</sub> /in
	Exterior Gypsum	3.26 lb <sub>f</sub> /in
Flame Spread and Smoke Development	ASTM E84	5
		5