

CERTIFICATION LETTER

We certify that ExoAir 220 has been tested against the following test methods/standards.

TYPICAL PHYSICAL PROPERTIES

Property	Test Method	Typical Values
Water Resistance	AATCC 127-2008	55 cm for 5 hours
Crack Bridging	ASTM C1305	Pass
Elongation	ASTM D412 Die C	900%
Tensile Strength	ASTM D412 Die C	325 psi
Nail Sealability	ASTM D1970 Section 7.9	Pass
Adhesion	ASTM D4541	Concrete 28 psi Sheathing 19 psi
Water Penetration Testing	ASTM E331	600 Pa (12.5 psf)
Air Permeance	ASTM E2178	0.0006 cfm/ft ² (0.012 L/sm ²) 75Pa (1.57 psf)
Air Leakage of Assembly	ASTM E2357	0.002 cfm/ft ² (0.012 L/sm ²) 75Pa (1.57 psf)
Assembly Evaluation of Fire Propagation Characteristics	NFPA 285	Successfully tested as part of a UL listed assembly

Property	Description
Type	Polymer-modified emulsion
Color	Black
Solids	60%
VOC	2 g/L
Thickness	70 wet mils; 40 dry mils
Storage	Keep from freezing
Application Temperature	40°F (4°C) and rising