

# EXOAIR® AIR BARRIER MEMBRANES

Impermeable Fluid Applied Membrane Comparison



MEMBRANE	EXOAIR® 120	EXOAIR® 130
Type	Asphaltic Emulsion	Synthetic Acrylic Emulsion
Standard Color	Black	White
Color Flexibility	No	Yes, custom colors available upon request
Mil Thickness	60 wet mils to achieve 40 dry	70 wet mils to achieve 40 dry
Coverage	25 square feet / gallon	23 square feet / gallon
Installation Temperature	40°F (4°C) and rising, 20 (-7°C) and rising when using co-spray	40°F (4°C) and rising
Co-Spray Option	Yes, Calcium Chloride	No
In-Service Temperature	Up to 158°F (70°C)	Up to 240°F (116°C)
UV Exposure	30 days	12 months
NFPA 285 Tested Assembly	No, options with stone wool, please contact Technical Service	Yes, variety of assemblies available in UL Directory and optional engineering analysis
Cone Calorimetry	Not Evaluated	Data available for engineering analysis
Flame Spread Smoke Development	Not Evaluated	15 25
Sealants adhere to cured surface	Dymonic® 100	Dymonic 100 & Spectrem® 1

Tremco Commercial Sealants & Waterproofing | 3735 Green Road | Beachwood, OH 44122 | US: 800.852.9068 | CAN: 800.363.3213 | tremcosealants.com

Tremco Construction Products Group (CPG) brings together Tremco Incorporated's Commercial Sealants & Waterproofing and Roofing & Building Maintenance operating divisions; Dryvit Systems, Inc.; Nudura Inc.; Willseal; Weatherproofing Technologies, Inc. and Weatherproofing Technologies Canada, Inc.



Tremco®, ExoAir®, Dymonic® and Spectrem® are registered trademarks of Tremco Incorporated. Use of the ® symbol indicates registration with the US Patent & Trademark Office and the Canadian Intellectual Property Office.

1120/EA120&130CS

tremcocpg.com