



APPLICATION INSTRUCTIONS

1. Purpose

1.1 The purpose of this document is to establish typical guidelines for installation of Willseal Color Coreseal-H. The techniques involved may require modifications to adjust to jobsite conditions. Consult your local Tremco Sales Representative or Tremco Technical Services for specific design requirements

2. Scope

2.1 This document will provide the necessary instructions for installation of Willseal Color Coreseal-H to qualify for a manufacturer's warranty.

3. Storage

3.1 Store materials in a dry, enclosed area, making sure materials are off the ground and out of direct sunlight

3.2 Material will expand faster when hot and slower when cold. In cold temperatures, store material in a heated area 24 hours prior to installation. In hot temperatures, store material out of direct sunlight and not in an enclosed storage container where temperatures may exceed 100°F.

4. Substrate Preparation

4.1 Verify that the joint is clean, sound, and will provide an appropriate surface for installation of the joint sealant

4.2 Use compressed air to clean any loose debris from the joint.

4.3 Apply water or alcohol to a clean cloth and wipe the joint walls to the depth of the sealant material plus 1"

4.4 Verify that the joint is uniform and repair any spalls prior to installation

4.5 Check the material for appropriate length, width, and depth

4.6 Supplied material will as a standard be over-sized 25% larger than the intended joint opening

4.7 Joint depth must allow for the installed material to be recessed 1/4" from the substrate surface

5. Application Procedure

5.1 When fully prepared to install, apply a 1/16" - 1/8" coating of the epoxy mixture to both joint walls using a 1" margin trowel to a depth of the sealant material plus 1/2"

5.2 The epoxy must still be wet upon installation of Willseal Color Coreseal-H;

5.3 The working time for epoxy is approximately 30 minutes depending on the temperature

5.4 If the epoxy hardens on the surface of the substrate before installation, another coat of epoxy can be applied within 2 hours. After 2 hours, the substrate surface must be abraded to eliminate the amine blush that occurs during the final cure

5.5 Recess joint 1/4" from the substrate surface

6. Joints, Sidewall and Finishing Work

6.1 Verify that the new piece of material is cut square and not at an angle to the previous piece installed

6.2 Apply supplied joint splice adhesive to the butt end of the new piece of material

6.3 Do not apply joint splice adhesive to the faces of the product that are in contact with the epoxy

6.4 Overlap extra material (approximately 1/2" - 1") at seams and splices to ensure that the seam is in compression after installation

6.5 Make sure seams are flush against each other and then push the pieces together

6.6 Butt seam all "T" and "+" intersections

6.7 Once the joint is installed, run and tool a 1/4" bead of the supplied silicone along both sides of the face of the joint along the substrate face

6.8 Run and tool the supplied silicone accessory over all seams and transitions to allow for a clean, aesthetic finish

6.9 Remove any excess adhesive material left on the surface of the material substrate; do not allow the excess adhesives to cure

0919/WCCSHAI

Please refer to our website at www.tremcosealants.com for the most up-to-date Application Instructions.

Tremco Commercial Sealants & Waterproofing

3735 Green Rd
Beachwood OH 44122
216.292.5000 / 800.321.7906

1451 Jacobson Ave
Ashland OH 44805
419.289.2050 / 800.321.6357

220 Wicksteed Ave
Toronto ON M4H1G7
416.421.3300 / 800.363.3213

1445 Rue de Coulomb
Boucherville QC J4B 7L8
514.521.9555