

Tremco Incorporated certifies that Superstop Waterstop bentonite waterstop material meets the physical properties outlined in the Tremco Incorporated published data sheets, specifications, and application instructions. This product has been tested against the following ASTM methods as shown herein:

Superstop Waterstop

Bentonite Waterstop Material

TYPICAL PHYSICAL PROPERTIES

PROPERTY	TEST METHOD	US VALUES	SI VALUES
Specific Gravity	ASTM D71	1.75	
Softening Point	ASTM D30	212 °F	100 °C
Flash Point	ASTM D93-97	None	
Application Temperature		0 to 120 °F	-17.8 to 110 °C
Service Temperature		-40 to 230 °F	-40 to 100 °C
Color		Gray	
Tear Strength		70 lb	31.7 kg
Water Flow through a concrete joint with 100' water head	ASTM D751 Method A	No Flow	