



Tremco Commercial Sealants & Waterproofing
 3735 Green Road
 Beachwood, OH 44122
 US: 800.852.9068
 Canada: 800.363.3213
 www.tremcosealants.com

We certify that ExoAir 2000 has been tested against the following test methods/standards.

TYPICAL PHYSICAL PROPERTIES

Property		Description
Color		Gray
Solids		0.71
Application		Spray, Roller, or Troweled
Thickness		28-30 mils
Storage Temperature		40 to 100° F (5 to 37° C)
Cure Time (75° F, 50% RH)		6 Hours
Skin Time (75° F, 50% RH)		2 Hours
Application Temperature		Above 25° F (-4° C) and rising
Property	Test Method	Typical Results
Hydrostatic Head	AATCC – 127	Pass
Crack Bridging	ASTM C1305	Pass
Elongation Tensile Strength	ASTM D412 Die C	250% 240 psi
Nail Sealability	ASTM D1970	Pass
Adhesion	ASTM D4541	16 psi <
Antifungal	ASTM D5590	Pass
Water Vapor Permeance	ASTM E96 Dry Cup ASTM E96 Wet Cup	1.79 US perms 16.91 US perms
Water Penetration	ASTM E331	Pass
Air Leakage of Material	ASTM E2178, Free Film Method @ 75 Pa	0.002 cfm/ft ² Passed at 6.27 lb/ft ² (300 PA) for 2 hours
Air Leakage of Assembly	ASTM E2357	0.0066 cfm/ft ² @ 1.56 lb/ft ² (0.013 L/(s•m ²) @ (75 pa)
Flame Spread Smoke Development	ASTM E84	5 0