



Tremco Commercial Sealants & Waterproofing
 3735 Green Road
 Beachwood, OH 44122
 US: 800.852.9068
 Canada: 800.363.3213
 www.tremcosealants.com

Tremco Incorporated certifies that Tremco 2550 asphalt protection board (1/8") meets the physical properties outlined in the Tremco Incorporated published data sheets, specifications, and application instructions. This product exhibits the typical physical properties as shown herein:

TYPICAL PHYSICAL PROPERTIES

Property	Typical Values
Puncture Resistance at 94° C	200 psi
Indentation	Less than 0.9 mm
Density, lb/ft ²	88 lb/ft ²
Weight, lb/ft ²	0.92
Bitumen Content, % by Weight	0.445
Inert Residual, % by Weight	0.55
Binders, Fiberglass (both sides)	Full Width Inorganic Non-Woven Matting
Binders, % inorganic	100%
Bitumen Softening Point °C	108° C
Anti-Stick Material	Polyethylene Film
Alkali Attack	No Disintegration
Binders, Tensile Strength	
Width, lb	24 lb
Length, lb	33 lb
Water Absorption, % Weight Increase (after 80 Hours at 60° C)	0.26%
Water Permeability (after 1 month)	No Leakage, Swelling or Deterioration