

Tremco Commercial Sealants & Waterproofing 3735 Green Road Beachwood, OH 44122 US: 800.852.9068

Canada: 800.363.3213 www.tremcosealants.com

We certify that ExoAir 210AT has been tested to the following ASTM standards and does conform to the specification requirements.

Property		Description	
Туре		Acrylic sheet with nonwoven facer	
Color		Gray	
Solids		100%	
Facer Basis Weight		2.95 oz/sy (110 gsm)	
Application		Self-Adhered	
Storage Temperature		40° to 100° F (5° to 37° C)	
Application Temperature		Above 20° F (-7° C) and rising.	
Service Temperature		Intermittent exposure up to 180° F (86° C)	
Property	Test N	1ethod	Typical Values
Maximum V.O.C	Method 310		2 g/L
Air Leakage of Material	ASTM E2178; Free Film Method		0.003 cfm/ft <sup>2</sup> (0.02 L/(s•m <sup>2</sup> ))
	@ 75 Pa		
			·

Property	Test Method	Typical Values
Maximum V.O.C	Method 310	2 g/L
Air Leakage of Material	ASTM E2178; Free Film Method	0.003 cfm/ft <sup>2</sup> (0.02 L/(s•m <sup>2</sup> ))
	@ 75 Pa	
Water Vapor Transmission	ASTM E96 Wet Cup	16.9 US Perms
Water Resistance	AATCC-127	Pass
Adhesion	ASTM D4541	22.9 psi
Resistance to Puncture	ASTM E154	≥40 lbf
Peel Adhesion	ASTM D3330 Method F	
	Stainless Steel	5.2 lb <sub>f</sub> /in
	Plywood	7.25 lb <sub>f</sub> /in
	OSB	4.25 lb <sub>f</sub> /in
	Exterior Gypsum	3.26 lb <sub>f</sub> /in
Flame Spread and Smoke	ASTM E84	5
Development		5