



Tremco Commercial Sealants & Waterproofing
 3735 Green Road
 Beachwood, OH 44122
 US: 800.852.9068
 Canada: 800.363.3213
 www.tremcosealants.com

We certify that Tremco Permaquik 200 Crystalline has been tested against the following ASTM methods and does conform to the specification requirements.

Physical Properties	Typical Values		Test Method
Hydrostatic Head Pressure	100' (28m)		
Compressive Strength	Days 3 7 28	PSI 4,145 5,560 6,970	ASTM C39
Water Permeability	6.6 x 10 ⁻¹² K, cm/sec		ASTM D5084
Water Vapor Transmission	0.12 perms		ASTM E96