

Tremco Commercial Sealants & Waterproofing 3735 Green Road Beachwood, OH 44122 US: 800.852.9068

Canada: 800.363.3213 www.tremcosealants.com

Tremco Incorporated certifies that TREMDrain® 2000 NW multi-composite drainage and protection boards meet the physical properties outlined in the Tremco Incorporated published data sheets, specifications, and application instructions. This product has been tested against the following ASTM methods as shown herein:

TYPICAL PHYSICAL PROPERTIES

Property	Test Method	Values US	Values SI
Typical Applications		Split Slab, Planters	
Roll Length		50′	15.24 M
Roll Width		4'	1.22 M
Roll Weight		54 lb	20.86 kg
Recycled Content		>60%	
<u>Fabric</u>			
Material		Nonwoven Needle-	
		Punched Polypropylene	
Weight	ASTM D3776	6 oz/yd²	203.43 g/M ²
Grab Tensile Strength	ASTM D4632	205 lb	1,090 N
CBR Puncture	ASTM D6241	580 lbs	2,580 N
Grab Elongation	ASTM D4632	60%	
AOS	ASTM D4751	80 sieve	0.180 mm
Permittivity	ASTM D4491	1.8 sec ⁻¹	
Water Flow Rate	ASTM D4491	135 gpm/ft ²	5,501 Lpm/m ²
Root Barrier Fabric		None	
UV Resistance	ASTM D4355	70%/500 Hrs	70%/500 Hrs
<u>Core</u>			
Material		Polystyrene	
Thickness	ASTM D1777	0.44 in	11 mm
Compressive Strength	ASTM D1621	18,000 lb/ft ²	862 kPa
	ASTM D6364	18,000 lb/ft ²	862 kPa
Backing Film		Yes	
In-Pane Flow Rate	ASTM D4716	18 gpm/ft	224 Lpm/m