



Tremco Commercial Sealants & Waterproofing  
 3735 Green Road  
 Beachwood, OH 44122  
 US: 800.852.9068  
 Canada: 800.363.3213  
 www.tremcosealants.com

Tremco Incorporated certifies that TREMDrain 6000 multi-composite drainage and protection boards meet the physical properties outlined in the Tremco Incorporated published data sheets, specifications, and application instructions. This product has been tested against the following ASTM methods as shown herein:

### TYPICAL PHYSICAL PROPERTIES

Property	Test Method	Values US	Values SI
<b>Typical Applications</b>			
Flow Capacity per unit width	ASTM D4716	18 gmp/ft	224 Lpm/M
Roll Length		50'	15.24 M
Roll Width		6'	1.8 M
<b>Fabric</b>			
Material		Polypropylene	
Weight	ASTM D3776		
Grab Tensile Strength	ASTM D4632	115 lbf	512 N
Puncture Strength	ASTM D4833	70 lb	311 N
Trapezoidal Tear	ASTMD4533		
Mullen Burst Strength	ASTM D3786		
Grab Elongation	ASTM D4632	70%	
AOS	ASTM D4751	70 sieve	0.21 mm
Flow Rate	ASTM D4491	150 gmp/ft <sup>2</sup>	6,112 Lpm/M <sup>2</sup>
Root Barrier Fabric		None	
UV Resistance	ASTM D4355	70%/500 hr	
<b>Core</b>			
Material		Polypropylene	
Thickness	ASTM D1777	0.4"	
Compressive Strength		15,000 lb/ft <sup>2</sup>	718 kPA