



Tremco Commercial Sealants & Waterproofing
 3735 Green Road
 Beachwood, OH 44122
 US: 800.852.9068
 Canada: 800.363.3213
 www.tremcosealants.com

Tremco Incorporated certifies that TREMDrain 6600 multi-composite drainage and protection boards for use in Tremco Bonded Systems in High Velocity Wind Zones meet the physical properties outlined in the Tremco Incorporated published data sheets, specifications, and application instructions. This product has been tested against the following ASTM methods as shown herein:

TYPICAL PHYSICAL PROPERTIES

| Property | Test Method | Values US | Values SI |
|------------------------------|-------------|--|--------------------------|
| Typical Applications | | Tremco horizontal bonded systems in high velocity wind zones | |
| Flow Capacity per unit width | ASTM D4716 | 21 gpm/ft | 261 Lpm/M |
| Roll Length | | 50' | 15.24 M |
| Roll Width | | 6' | 1.8 M |
| Roll Weight | | | |
| Fabric | | | |
| Material | | Nonwoven Needle-Punched Polypropylene | |
| Grab Tensile Strength | ASTM D4632 | 160 lbf | 712 N |
| Grab Elongation | ASTM D4632 | 70% | |
| AOS | ASTM D4751 | 70 sieve | 0.21 mm |
| Flow Rate | ASTM D4491 | 110 gpm/ft ² | 4,483 Lpm/M ² |
| Root Barrier Fabric | | None | |
| UV Resistance | ASTM D4355 | 70%/500 Hr | |
| CBR Puncture Strength | ASTM D6241 | 450 lb | 200 kN |
| Core | | | |
| Material | | Polypropylene | |
| Thickness | ASTM D1777 | 0.4" | |
| Compressive Strength | | 18,000 lb/ft ² | 862 kPa |