



Tremco Commercial Sealants & Waterproofing
 3735 Green Road
 Beachwood, OH 44122
 US: 800.852.9068
 Canada: 800.363.3213
 www.tremcosealants.com

Tremco certifies that the Vulkem® 801 Elastomeric Coating System has been tested with the following Typical Physical Properties.

TYPICAL PHYSICAL PROPERTIES

Property	Test Method	Typical Value
Tensile Strength	ASTM D412	280 psi (1.9 MPa)
Elongation	ASTM D412	375%
Hardness "A"	ASTM C836	75
Artificial Weathering	ASTM G23	Excellent
Water Absorption	ASTM C739	Nil
Extension/Compression	ASTM C957	Passes
% Recovery	ASTM C957	94%
Permeability	ASTM E96	0.095
Cure Time	ASTM D1640	10-12 Hours