

PRODUCT DESCRIPTION

Vulkem® 350NF/951NF/951NF is a modified polyurethane traffic deck coating system composed of a base coat (350NF), heavy duty intermediate coat (951NF) and a top coat (951NF). This unique waterproofing system is designed to have tenacious adhesion, extreme impact, and abrasion resistance along with remarkable chemical stability. The elastomeric properties of the system’s components enable the complete assembly to give and work with the concrete slab, bridging the shrinkage cracks.

Vulkem 350NF Base Coat is a single-component, low odor, low VOC, urethane membrane that bonds firmly to clean, dry concrete and metal. It retains its integrity even if substrate movement causes hair-line cracks of up to 1/16” (1.5 mm). If cut or damaged, Vulkem 350NF is available in roller (R) and in self-leveling (SL) grade for vertical and horizontal applications.

Vulkem 951NF Intermediate Coat is an aliphatic, low VOC, two-component urethane that is applied after the Vulkem 350NF Base Coat has cured. The intermediate coat is loaded with aggregate to give the system excellent impact, abrasion, and chemical resistance.

Vulkem 951NF Top Coat is an aliphatic, low VOC, two-component polyurethane that is applied after then Vulkem 951NF intermediate coat has cured. Interlaminary adhesion to Vulkem 951NF is exceedingly strong. The top coat affords excellent abrasion resistance, UV stability and chemical resistance to complete with Vulkem Traffic Deck Coating System.

BASIC USES

Vulkem 350NF/951NF/951NF is a cold-applied traffic deck coating system designed for waterproofing concrete slabs and protecting occupied areas underneath from water damage. Additionally, the system will protect the concrete from the damaging effects of water, deicing salts, chemicals, gasoline, oils, and anti-freeze.

SEALANT · WATERPROOFING & RESTORATION INSTITUTE	
Issued to: Tremco Incorporated	
Product: Vulkem 360 NF Basecoat & Vulkem 951 NF Topcoat	
ASTM D 412: Tensile Strength of Top Coat Vulkem 951 NF Topcoat Tensile Strength: 5,394 psi; Elongation: 294% Pass ✓	
ASTM D 4541: Adhesion of Base Coat Vulkem 360 NF Basecoat Pull-off Adhesion: 363 psi Pass ✓	
ASTM D 4060: Abrasion Resistance of Top Coat Vulkem 360 NF Basecoat Abrasion Resistance: 20 mgms loss – mgms loss/1,000 cycles Pass ✓	
Validation Date: 04/27/22 – 04/26/27	
No. 422–VUL360 Copyright © 2022	
DECK COATING VALIDATION www.swrionline.org	

SEALANT · WATERPROOFING & RESTORATION INSTITUTE	
Issued to: Tremco CPG Inc.	
Product: Vulkem® 350FC/Vulkem 951NF	
ASTM D 412: Tensile Strength of Top Coat Vulkem® 951NF Topcoat Tensile Strength: 4,392 psi; Elongation: 258% Pass ✓	
ASTM D 4541: Adhesion of Base Coat Vulkem® 350FC SL Pull-off Adhesion: 472 psi Pass ✓	
ASTM D 4060: Abrasion Resistance of Top Coat Vulkem® 951NF Abrasion Resistance: 12 mg loss – mg loss/1,000 cycles Pass ✓	
Validation Date: 2/10/23 – 2/09/28	
No. VUL350–VUL951 Copyright © 2023	
DECK COATING VALIDATION www.swrionline.org	

SEALANT · WATERPROOFING & RESTORATION INSTITUTE	
Issued to: Tremco Incorporated	
Product: Vulkem 350 NF Basecoat & Vulkem 346 Topcoat	
ASTM D 412: Tensile Strength of Top Coat Vulkem 346 Topcoat Tensile Strength: 3,236 psi; Elongation: 191% Pass ✓	
ASTM D 4541: Adhesion of Base Coat Vulkem 350 NF Basecoat Pull-off Adhesion: 259 psi Pass ✓	
ASTM D 4060: Abrasion Resistance of Top Coat Vulkem 350 NF Basecoat Abrasion Resistance: 48 mgms loss – mgms loss/1,000 cycles Pass ✓	
Validation Date: 04/27/22 – 04/26/27	
No. 422–VUL350 Copyright © 2022	
DECK COATING VALIDATION www.swrionline.org	

FEATURES & BENEFITS

- Fast cure through time allows for use 24 hr after installation.
- Low odor and low level of Volatile Organic Compounds (VOC) provides for use in neighbor friendly, inhabited structures.

- Mildew and fungus resistance safeguards concrete surfaces against environmental contaminants.
 - Excellent durability and UV resistance extends the useful life of vehicular systems.
 - Recoatable and compatible with other Tremco sealants and expansion joints, enhance waterproofing protection with full system compatibility.
-

AVAILABILITY

Immediately available from your local Tremco Sales Representative, Tremco distributor, or warehouse.

PACKAGING

Vulkem 350NF: 5-gal (18.9-L) pails, 55-gal (208.2-L) drums

Vulkem 951NF: Total of 4.6-gal kit – Part A 3.75 gal (14.2 L) in a 5-gal (18.9-L) pail, Part B 0.85 gal (3.2 L) in a 1-gal pail.

COLORS

Vulkem 951NF is available in Beige, Gray, Limestone, Black, and Slate Gray. Made-to-order and special colors are also available upon request.

INSTALLATION

Concrete shall be water-cured and attain a 4000 psi minimum compressive strength. Concrete finish shall be a light steel trowel followed by a fine-hair broom, or equivalent ICRI #2-#4 finish. Moisture content in the concrete must be lower than 4.5% as measured by a Tramex CME 4 Moisture Meter. Depending on concrete construction and job site location, additional concrete testing may be required. Please contact your local Tremco Sales or Technical Representative.

Please refer to the Vulkem 350NF/951NF/951NF Application Instructions for complete application details. The techniques involved may require modification to adjust to the jobsite conditions. Consult your Tremco Sales Representative or Tremco Technical Service for site conditions and requirements.

FIRE RATED ASSEMBLIES

ANSI/UL790 – Standard Test Methods for Fire Tests of Roof Coverings

CAN/ULC-S107 – Methods of Fire Tests of Roof Coverings

APPLICABLE STANDARDS

Conforms to:

- ASTM C957
 - CSA S413-14
-

LIMITATIONS

- Do not apply to damp or contaminated surfaces.
 - Use with adequate ventilation.
 - Substrate must be at least 5 °F (3 °C) above the measured dew point temperatures to avoid dew point conditions.
-

WARRANTY

Tremco warrants its Products to be free of defects in materials but makes no warranty as to appearance or color. Since methods of application and on-site conditions are beyond our control and can affect performance, Tremco makes no other warranty, expressed or implied including warranties of MERCHANTABILITY and FITNESS FOR A PARTICULAR PURPOSE with

respect to Tremco Products. Tremco's sole obligation shall be, at its option, to replace or refund the purchase price of the quantity of Tremco Products proven to be defective, and Tremco shall not be liable for any loss or damage.

TYPICAL PHYSICAL PROPERTIES				
PROPERTY	TEST METHOD	VULKEM 350NF	VULKEM 951NF	VULKEM 951NF
Flash Point	Set-A-Flash	>160 °F (71 °C)	>200 °F (93 °C)	>200 °F (93 °C)
% Solids (by Weight)	ASTM D1353	90 to 98%	80 to 85%	80 to 85%
Drying Time @ 75 °F, 50% RH	ASTM D1640	25 mil film, 4 to 6 hr	12 mil film, 2 to 4 hr	12 mil film, 2 to 4 hr
Open to vehicular traffic		N/A	N/A	24 hr after cure
Weathering	ASTM D822	N/A	No effect	No effect
Salt Spray	ASTM B117	N/A	No effect	No effect
Viscosity	Brookfield C&P	4000 to 6000 cps	25000 cps	2500 cps
Elongation	ASTM D412	600 to 700%	145%	145%
Tensile Strength	ASTM D412	220 to 460 psi	4500 psi	4500 psi
Hardness (Shore A)	ASTM D2240	45 to 60	50 shore D	50 shore D
Adhesion (Peel Strength)	ASTM D903	Unprimed concrete, 20 to 30 pli, 100% cohesive failure	100% cohesive failure	100% cohesive failure
Adhesion (Pull-Off)	ASTM D4541	150 to 200 psi	N/A	N/A
Abrasion Resistance (1000 cycles)	ASTM D4060	N/A	33 mg	33 mg
Accelerated Aging	ASTM D573	No loss of elongation or tensile strength	No loss of elongation or tensile strength	No loss of elongation or tensile strength
*Accelerated aging test. 1 daily cycle of UV and water spray greatly exceeds 1 day of real world exposure. Contact Tremco Technical Service or your local sales representative for more information.				

Tremco Construction Products Group (CPG) brings together Tremco CPG Inc. and its Dryvit and Nudura brands; Willseal; Prebuck LLC; Tremco Barrier Solutions, Inc.; Weatherproofing Technologies, Inc. and its Pure Air Control Services and Canam Building Envelope Specialists offerings; and Weatherproofing Technologies Canada, Inc.



tremcosealants.com | 800.321.7906



Construction Products Group

3735 Green Rd. | Beachwood, OH 44122
800.321.7906 | tremcocpg.com