

## PRODUCT DESCRIPTION

Vulkem® 360NF/346/346 is a modified polyurethane traffic deck coating system composed of a base coat (360NF), heavy duty intermediate coat (346) and a top coat (346). This unique waterproofing system is designed to have tenacious adhesion, extreme impact, and abrasion resistance along with remarkable chemical stability. The elastomeric properties of the system's components enable the complete assembly to give and work with the concrete slab, bridging the shrinkage cracks.


Vulkem 360NF Base Coat is a low-odor, low-VOC, water-cured, rapid setting urethane membrane that bonds firmly to clean, dry concrete and metal. It retains its integrity even if substrate movement causes hair-line cracks of up to 1/16" (1.5 mm). If cut or damaged, Vulkem 360NF will prevent water migration between itself and the substrate.

Vulkem 346 Intermediate Coat is an aliphatic one-component urethane that is applied after the Vulkem 360NF Base Coat has cured. The intermediate coat is loaded with aggregate to give the system excellent impact, abrasion, and chemical resistance.

Vulkem 346 Top Coat is an aliphatic one-component polyurethane that is applied after the Vulkem 346 intermediate coat has cured. Interlaminary adhesion to Vulkem 346 is exceedingly strong. The top coat affords excellent abrasion resistance, UV stability and chemical resistance to complete this Vulkem Traffic Deck Coating System.

## BASIC USES

Vulkem 360NF/346/346 is a cold-applied traffic deck coating system designed for waterproofing concrete slabs and protecting occupied areas underneath from water damage. Additionally, the system will protect the concrete from the damaging effects of water, deicing salts, chemicals, gasoline, oils, and anti-freeze.



**SEALANT · WATERPROOFING  
& RESTORATION INSTITUTE**

**Issued to: Tremco Incorporated**  
**Product:** Vulkem 350 NF Basecoat & Vulkem 346 Topcoat

**ASTM D 412:** Tensile Strength of Top Coat  
Vulkem 346 Topcoat  
Tensile Strength: 3,236 psi;  
Elongation: 191% Pass ✓

**ASTM D 4541:** Adhesion of Base Coat  
Vulkem 350 NF Basecoat  
Pull-off Adhesion: 259 psi Pass ✓

**ASTM D 4060:** Abrasion Resistance of Top Coat  
Vulkem 350 NF Basecoat  
Abrasion Resistance: 48 mgms loss  
– mgms loss/1,000 cycles Pass ✓

**Validation Date:** 04/27/22 – 04/26/27  
**No. 422-VUL350** Copyright © 2022

**DECK COATING VALIDATION**  
[www.swrionline.org](http://www.swrionline.org)

## FEATURES & BENEFITS

- Fast cure through time allows for use 72 hr after installation.
- Mildew and fungus resistance safeguard concrete surfaces against environmental contaminants.
- Excellent durability and UV resistance extends the useful life of vehicular systems.

- Recoatable and compatible with other Tremco sealants and expansion joints, which enhance waterproofing protection with full system compatibility.
- 

## AVAILABILITY

Immediately available from your local Tremco Sales Representative, Tremco distributor, or warehouse.

---

## PACKAGING

Vulkem 360NF: 5 gal (18.9 L) in a 6-gal (22.7-L) pail

Vulkem 346: 5-gal (18.9-L) pails, 55-gal (208.2-L) drums

---

## COLORS

Vulkem 346 is available in Gray, Limestone, Slate Gray, \*Black, \*White, \*Beige, and \*Maple. Made-to-order and special colors are also available upon request.

\*Denotes special color.

---

## FIRE RELATED ASSEMBLIES

ANSI/UL790 – Standard Test Methods for Fire Tests of Roof Coverings

CAN/ULC-S107 – Methods of Fire Tests of Roof Coverings

---

## INSTALLATION

Concrete shall be water-cured and attain a 4000 psi minimum compressive strength. Concrete finish shall be a light steel trowel followed by a fine-hair broom, or equivalent ICRI #3-#4 finish. Moisture content in the concrete must be lower than 4.5% as measures by a Tramex CME 4 Moisture Meter. Depending on concrete construction and job site location, additional concrete testing may be required. Please contact your local Tremco Sales or Technical Representative.

Please refer to the Vulkem 360NF/346/346 Application Instructions for complete application details. The techniques involved may require modification to adjust to the jobsite conditions. Consult your Tremco Sales Representative or Tremco Technical Service for site conditions and requirements.

---

## APPLICABLE STANDARDS

Conforms to

- ASTM C957
  - UL 790 – Class A Fire Rating for non-combustible substrates
  - CSA S413-14
- 

## LIMITATIONS

- Do not apply to damp or contaminated surfaces.
  - Use with adequate ventilation.
  - Substrate must be at least 5 °F (3 °C) above the measured dew point temperatures to avoid dew point conditions.
- 

## WARRANTY

A repair or replacement warranty is available on all Tremco products. Visit <https://www.tremcosealants.com/warranties/> for details.

TYPICAL PHYSICAL PROPERTIES				
PROPERTY	TEST METHOD	VULKEM 360NF	VULKEM 346	VULKEM 346
Flash Point	Set-A-Flash	185 °F (85 °C)	85 °F (29 °C)	85 °F (29 °C)
% Solids (by Weight)	ASTM D1353	91%	72%	72%
Drying Time @ 75 °F, 50% RH	ASTM D1640	25 mil film, 6 to 12 hr	15 mil film, 6 to 8 hr	15 mil film, 6 to 8 hr
Open to vehicular traffic		N/A	72 hr after cure	72 hr after cure
Weathering	ASTM D822	N/A	No effect	No effect
Salt Spray	ASTM B117	N/A	No effect	No effect
Viscosity	Brookfield C&P	8000 to 10000 cps	2000 to 3000 cps	2000 to 3000 cps
Elongation	ASTM D412	500%	120%	120%
Tensile Strength	ASTM D412	275 psi	2800 psi	2800 psi
Hardness (Shore A)	ASTM D2240	40 to 50	85 to 95	85 to 95
Adhesion (Peel Strength)	ASTM D903	Unprimed concrete, 45 pli, 100% cohesive failure	100% cohesive failure	100% cohesive failure
Adhesion (Pull-Off)	ASTM D4541	350 psi	N/A	N/A
Abrasion Resistance (1000 cycles)	ASTM D4060	N/A	50 mg	50 mg
Accelerated Aging	ASTM D573	No loss of elongation or tensile strength	No loss of elongation or tensile strength	No loss of elongation or tensile strength
*Accelerated aging test. 1 daily cycle of UV and water spray greatly exceeds 1 day of real world exposure. Contact Tremco Technical Service or your local sales representative for more information.				

Please refer to our website at [www.tremcosealants.com](http://www.tremcosealants.com) for the most up-to-date Product Data Sheets.

**NOTE: All Tremco Safety Data Sheets (SDS) are in alignment with the Globally Harmonized System of Classification and Labelling of Chemicals (GHS) requirements.**

V360NF346346/0323

Tremco Construction Products Group (CPG) brings together Tremco CPG Inc. and its Dryvit and Nudura brands; Willseal; Prebuck LLC; Tremco Barrier Solutions, Inc.; Weatherproofing Technologies, Inc. and its Pure Air Control Services and Canam Building Envelope Specialists offerings; and Weatherproofing Technologies Canada, Inc.



[tremcosealants.com](http://tremcosealants.com) | 800.321.7906



Construction Products Group

3735 Green Rd. | Beachwood, OH 44122  
800.321.7906 | [tremcocpg.com](http://tremcocpg.com)